



CERAMIC FIBER BLANKET

TECHNICAL DATA SHEET



Ceramic Fiber Blanket

Specification Temp.(°C)	1260	1400
Rate of Liner(%) (24h,density 128kg/m3)	-3 (1000°C)	-3(1250°C)
Rate of Thermal Conductivity(w/n.k) (density 128kg/m3)	0.09(400°C) 0.16(800°C)	0.12(600°C) 0.20(1000°C)
Tensile Strength(Mpa) (density 128kg/m3)	0.04	0.04





TRUESEAL PACIFIC CO.,LTD.

**TRUE SEAL
PACIFIC**

