



TrueSeal Pacific

1561 SOI LADPRAW 94 SRIWARA RD., WANGTONGLANG, SUB DISTRICT,
 WANGTONGLANG DISTRICT, BANGKOK 10310 THAILAND
 TEL : 02-5590174-75, 02-5592425-27 FAX : 02-5592314

SPECIFICATION OF NEOPRENE RUBBER SHEET

Description	General Properties				Heat resistance 130°C x 70h			Oil ASTM NO.1 resistance 100°C x 70h		Compression set 70 °C x 22h (%)	General Information
	Hs (Shore A)	T _B (kg/cm ²)	PSI	E _B (%)	ΔHs (Shore A)	ΔV (%)	E _B (%)	ΔHs (Shore A)	ΔV (%)		
Neoprene(CR) Rubber Sheet	70±5	100	1430	350	+15	-40	-50	±10	±10, -5	40	Weatherability heat resistance, fire resistance and resistance to petroleum based fluids